

GEROthem[®] energy piles

GEROthem[®] pipe made of PE100-RC (with significantly increased crack resistance), black, SDR11 / PN16. Proof of suitability for installation without a sand bed via FNCT in accordance with DVS 2203-4 Addendum 2 (required minimum service life of > 8,760 hrs for each raw material batch, test conditions: 80°C, 4 N/mm², 2% Arkopal N-100).

Mass and quality requirements according to DIN 8074/8075,
Delivery as coils

Pipe dimensions: de 25 × 2.3 mm
Delivery length: 50 m, 100 m, 200 m
Art. No.:
Quantity:

Pipe dimensions: de 32 × 3.0 mm
Delivery length: 50 m, 100 m, 200 m
Art. No.:
Quantity:

Pipe dimensions: de 40 × 3.7 mm
Delivery length: 50 m, 100 m, 200 m
Art. No.:
Quantity:

Note: other lengths available on request

GERO^{therm}® energy piles, short probes, registers

GERO^{therm}® pipe PE100-RC (with significantly increased crack resistance), black, SDR11 / PN16. Proof of suitability for installation without a sand bed via FNCT in accordance with DVS 2203-4 Addendum 2 (required minimum service life of > 8,760 hrs for each raw material batch, test conditions: 80°C, 4 N/mm², 2% Arkopal N-100). Mass and quality requirements according to DIN 8074/8075, Delivery as short probes or registers.

As short probes: de 25 × 2.3 mm

Delivery length: as required

Art. No.:

Quantity:

As short probes: de 32 × 3.0 mm

Delivery length: as required

Art. No.:

Quantity:

As short probes: de 40 × 3.7 mm

Delivery length: as required

Art. No.:

Quantity:

As register W or WV or WW: de 25 × 2.3 mm

Delivery length: as required, e.g. as W 14-12-14 m

Art. No.:

Quantity:

As register W or WV or WW: de 32 × 3.0 mm

Delivery length: as required, e.g. as W 14-12-14 m

Art. No.:

Quantity:

As register W or WV or WW: de 40 × 3.7 mm

Delivery length: as required, e.g. as W 14-12-14 m

Art. No.:

Quantity: