




Technical data sheet

GERO^{therm}® FLUX

The conical, safety- and pressure
loss-optimised geothermal probe
PN14 up to PN32
dn 43 x 3,5 - 6,5

GERO[®]therm[®] FLUX the conical, safety- and pressure loss-optimised geothermal probe

PN14 up to PN32 @ 20°C

Material	Polyethylene PE100-RC (resistance to cracking) and polyamide PA12
Geothermal probe design	- Two geothermal probe feet, PN40, U-shaped with dirt trap and a minimal pressure drop of <10 mbar at 1.0 m/s, and a fixture for securing weights as an aid to installation, plus a reinforcement brace for the GERO[®]therm[®] PUSH-FIX impact-resistant sleeve. - Four conical pipes for double-U probes from pipe series PN14 up to PN32 @20°C made of the material PE100-RC in the pipe outside diameter 43 × 3.5-6.5 mm with double metering and flow direction indication (forward/return flow)
Installation and operation	The part of the geothermal system down in the soil must withstand the pressures and temperatures that occur. The applicable standards must be observed.
Delivery form	Rolls on a pallet covered with protective film: each individual probe foot packed in a protective pouch with a factory certificate and serial number in accordance with EN 10204 2.2.
Regulations	SIA 384/6; SKZ HR3.26 A724; VDI 4640; DIN EN 12201-2; patent: EP 2 706 308
Geothermal probe signing	{Direction of flow} {GERO [®] therm FLUX} {Erdwärmesonde/Geothermal probe} {Swiss made} {EP 2 706 308} {43x3.5-6.5} {PE100-RC} {SDR14.3-6.6} {PN14-32} {Tmax40°C} {DIN EN 12201-2} {SKZ A724} {Part No.} {Maschine No.} {Date} {Production No.} {Double metering}
External monitoring	SKZ (Süddeutsches Kunststoffzentrum, Würzburg/Germany)
Physical properties	
Density	0.95 – 0.97 g / cm ³
Pipe roughness	0.03 mm
Minimum bending radius at 0°C	50 x dn
Minimum bending radius at 10°C	35 x dn
Minimum bending radius at 20°C	20 x dn
Mechanical properties	
Tensile modulus of elasticity (23°C, v = 1 mm/min, secant)	900 MPa
Yield stress (23°C, v = 50 mm/min)	23 MPa
Tensile deformation (23°C, v = 50 mm/min)	9 %
FNCT (4.0 MPa, 2% Arkopal N100, 80°C)	>/= 8760 h
Failure strain	>/= 350%
Mean thermal coefficient of linear thermal expansion	0.18 mm/m K
Hardness	
Shore hardness (Shore D (3 sec))	63
Thermal properties	
Maximum temperature	+ 40°C
Minimum temperature	- 20°C
Thermal conductivity	~0.4 W/mK
Specific thermal capacity	1.9 J/g K
Chemical properties	
The HakaGerodur GERO [®] therm [®] geothermal systems are resistant to the common heat transfer media. Refer to the Technical Manual for the suitable heat transfer media.	